



Tailored for tire and rubber performance –
Our range of phenolic and amino resins

Products	Characteristics	Dynamic viscosity 50% in MP ¹ [mPas] DIN 53177 23 °C	Softening point ring & ball [°C] DIN EN ISO 4625-1 5 °C/min	Content of free phenol [%] DIN EN ISO 8974	Properties	Uses
REINFORCING RESINS						
ALNOVOL® PN 160	Modified non-self-curing phenol novolac	700-1100	101-113	< 1.0	Suitable for reinforcing natural rubber, styrene butadiene rubber, EPDM rubber and nitrite rubber	Reinforcement of rubber
ALNOVOL® PN 320	Non-self-curing phenol novolac	1400-2200	108-120	< 0.3	High viscosity, very low free phenol	Reinforcement of rubber
ALNOVOL® VPN 1132	Modified non-self-curing phenol novolac	100-600	115-155	< 1.0	High tear resistance	Reinforcement of rubber
ADHESION PROMOTER						
ALNOVOL® PN 760	Functionalized phenol resin	800-1800	95-115	< 1.0	Very good aging, improved adhesion, environmentally friendly	Textile and steel cord adhesion promoter
ALNOVOL® PN 870	Functionalized phenol novolac	1000-2000	110-125	< 0.3	Excellent adhesion, resorcinol-free and cobalt-free compounding	Steel cord adhesion promoter
ALNOVOL® PN 871	Functionalized phenol novolac	1000-2000	110-125	< 0.3	High reactivity, excellent adhesion, resorcinol-free and cobalt-free compounding	Steel cord adhesion promoter
PERFORMANCE RESINS						
ALNOVOL® PN 330	Non-self-curing phenol novolac	1400-2200	108-120	< 0.3	Increasing wear resistance and chip & chunk	Performance resin for TBR and OTR tread compounds

Products	Characteristics	Content of HMMM ² Content of ash ³ [%]	Carrier type	Properties	Uses
ADHESION PROMOTER/CROSSLINKER					
CYREZ® 963 FAMILY	Hexamethoxymethyl melamine resin	> 98 ²	None	Low content of free formaldehyde	Curing agent for resorcinol and novolac resins
CYREZ® 964 FAMILY	Hexamethoxymethyl melamine resin	31-35 ³	Precipitated amorphous silica	Good flow ability, easily dispersible	Curing agent for resorcinol and novolac resins
CYREZ® RH-65	Hexamethoxymethyl melamine resin	31-35 ³	Rice husk silica	Bio based raw material, good flow ability, easily dispersible	Curing agent for resorcinol and novolac resins
CYREZ® CRA FAMILY	Hexamethoxymethyl melamine resin	24-28 ³	Precipitated amorphous silica	High loading, easily dispersible	Curing agent for resorcinol and novolac resins
CYREZ® CRA 400 EC	Hexamethoxymethyl melamine resin	24-28 ³	Precipitated amorphous silica	Ultra-low content of free formaldehyde, high loading, easily dispersible	Curing agent for resorcinol and novolac resins

Products	Characteristics	Content of ash ³ [%]	Carrier type	Properties	Uses
OTHERS					
ALNOVOL® UF 410 RPC	Carbamid resin	31-35 ³	Precipitated amorphous silica	Oil replacement, hardness improvement, low Mooney viscosity	Apex, bead, textile cord adhesion compounds
EBECRYL® TMPTMA	Trimethylolpropan-trimethacrylat	0	None	Coagent for peroxide crosslinking of elastomers	Technical rubber goods

1 MP: Methoxy propanol
Product availability can vary by usage location. Please contact your local allnex representative regarding availability in specific countries and regions



Contact:
Roberto Blanco Trillo
Email:
Roberto.Blanco-Trillo@allnex.com



Want to know more?
The QR-code leads to our web page where you'll find more information.

www.allnex.com

Disclaimer: allnex Group companies (allnex) exclude all liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge but does not constitute any express or implied guarantee or warranty as to the accuracy, the completeness or relevance of the data set out herein. Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is suitable for any specific use, performance or result. Any unauthorized use of the product or information may infringe the intellectual property rights of allnex, including its patent rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights or misappropriation of trade secrets of allnex and/or third parties remain the sole responsibility of the user.

Notice: Trademarks indicated with ® , TM or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex Netherlands B.V. or its directly or indirectly affiliated allnex Group companies.

©2025 allnex Group. All Rights Reserved.



Allnex Management GmbH
The Squire 13, Am Flughafen
60549 Frankfurt am Main, Germany



Keeping performance
rolling with advanced
additives

Amino and phenolic resins for
tire and rubber manufacturing

www.allnex.com

INNOVATIVE CHEMISTRY
FOR ALL NEX-T GENERATIONS

Specialty resins – The secret to better tires and rubbers

Helping you drive innovation

As a leading global manufacturer of specialty resins, allnex supports tire manufacturers with an industry-leading offering of advanced, eco-friendly additives. With ALNOVOL® and CYREZ®, our broad range of technical additives includes two co-reactant resins that are specifically designed for the needs of the tire industry and also boost performance in other types of rubber compounding and processing.

ALNOVOL® resins for tire compounding

With profound expertise dating back to the beginnings of phenolic chemistry in the 1950s, allnex has established itself as the producer of a well-rounded and widely respected offering of phenolic and functionalized resins for tire compounding.

It is this expertise which today allows us to offer tire makers our ALNOVOL® functionalized phenolic resins as a highly effective replacement for problematic adhesion systems. Long the industry standard for steel and tire cord integration but linked with odor issues and environmental drawbacks, these systems can now be substituted with a high-performing alternative. To meet the industry's demand for the removal of chemicals of concern, allnex also offers resorcinol- and cobalt-free options.

By reducing the expense associated with adhesion promoter systems, these new resins can bring significant cost savings. Sold globally and available in various package sizes, ALNOVOL® resins are manufactured in:

- **Germany:** Wiesbaden
- **USA:** Kalamazoo, MI
- **China:** JiaXing

CYREZ® resins for better adhesion and crosslinking

CYREZ® resins are among the industry's best-known performance compounds and used by major tire producers worldwide. They function either as adhesion promoters for steel cord in the breaker compound or as crosslinkers in various applications. allnex has been at the forefront of melamine resin development (HMMM, or hexamethoxymethylmelamine), broadening its use in tire compounds. CYREZ® resins are available in both liquid form and as a powder blend on a silica carrier. They are manufactured at seven of our plants worldwide:

- **USA:** Wallingford, CT
- **Norway:** Lillestrøm
- **Netherlands:** Botlek
- **Japan:** Shimonoseki
- **Brazil:** Ponta Grossa
- **China:** Zhuhai

Bonded to last – Resins that keep excellence on track

The “polymer backbone” of well-crafted tires

High-performance resins and adhesion promoters are at the heart of tire construction. From reinforcing compounds that boost wear resistance and hardness to adhesion systems that ensure tight bonds to cord layers, our advanced ALNOVOL® and CYREZ® additives play a critical role. These specialized solutions enhance durability, reduce environmental impact and address evolving industry demands for efficiency and sustainability.

ALNOVOL® additives for strength and sustainability

Product name	Adhesion promoter	Reinforcement
ALNOVOL® PN 160	■	■■■
ALNOVOL® PN 320	■■	■■
ALNOVOL® PN 760	■■■	■
ALNOVOL® UF 410 RPC		■■■■
ALNOVOL® PN 870	■■■	■
ALNOVOL® PN 330		■■

CYREZ® additives for bonds that go the distance

Product name	HMMM hardener	Material
CYREZ® 963	■	100% HMMM
CYREZ® 964	■	65% HMMM + silica
CYREZ® CRA 200	■	72% HMMM + silica
CYREZ® CRA 400 EC	■	65% HMMM + silica
CYREZ® ECO 965	■	65% HMMM + rice husk silica

